



CEMENT

Three Gang Moulds

PRODUCT CODE

NT-CE2980 40x40x160 mm, three gang mould
NT-CE2981 50x50x50 mm, three gang mould

STANDARDS

EN 196-1, ASTM C109

SPECIFICATIONS

The special designed molds used for cement compression and flexural tests are made of steel, and all parts are numbered.

In accordance with the EN 196-1 standard, samples are first subjected to flexural testing using 40x40x160 mm molds. Following the flexural testing, the remaining portions are then subjected to cement compression testing.



www.noustest.com

ADDRESS:İvedik OSB, 1462. Sk. No:24, 06374
İvedik Osh Yenimahalle - Ankara / Türkiye

info@noustest.com